

STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

ONTARIO BUILDING CODE ENGINEERING EVALUATION REPORT

Date 2021-12-31
File No. 0078-6-3-5764
For Trex Company, Inc.

Address | 160 Exeter Dr., Winchester, VA 22603-8605

Subject

Trex Transcend® Railing

Evaluation Scope

This report is provided to assist registered design professionals and building officials in Canada with determining compliance to the performance objectives in the named building codes.

The material(s) and system(s) described herein have been evaluated to the 2012 (w/ 2020 amendments) Ontario Building Code (OBC), Division A, Sections 1.2.1.1.(1)(a) and 1.2.1.1.(1)(b) for compliance with the objectives and functional statements attributed to the applicable acceptable solutions in Division B, for buildings classified under Part 3/4/5 and Part 9 construction.

CSI DIVISION: 06 00 00 WOOD, PLASTICS, AND COMPOSITES

SUBDIVISION: 06 81 00 Composite Railings

CSI DIVISION: 05 00 00 METALS **SUBDIVISION:** 05 52 00 Metal Railings

CODE SECTIONS AND STANDARDS:

OBC Div. B Section	<u>Description</u>	Referenced Standard or Div. B Section ¹	<u>Year</u>
3.3.1.17	All Floor Areas, Guards	-	-
3.3.5.9	Industrial Occupancy, Guards	-	-
3.4.6.6	Types of Exit Facilities, Guards	-	-
4.1.1.5	Structural Loads and Procedures, Design Basis	-	-
4.1.3.2.(2)	Limit States Design, Strength and Stability	Table 4.1.3.2A	2015
4.1.3.4	Limit States Design, Serviceability	4.1.3.5	2015
4.1.3.5	Limit States Design, Deflection	-	-
4.1.5.14	Loads on Guards and Handrails	-	-
4.1.7	Wind Load	-	-
4.3.1.1	Design Basis for Wood	CSA O86	2014
4.3.1.3	Termites	9.3.2.9	2015
4.3.5.1	Design Basis for Aluminum	CSA S157	2005

BOCA ENGINEERING CO. · (778) 265-1507, info@bocaengineering.com 203-1001 Cloverdale Ave, Victoria, BC, V8X 4C9



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

OBC Div. B Section	<u>Description</u>	Referenced Standard or Div. B Section ¹	<u>Year</u>
9.3.2.9.(6)(c)(i)	Termite and Decay Protection	CAN/CSA-O80.1	2008
9.4.1.1.(1)(c)(i)	Structural Design Requirements and Application Limits	Part 4	2015
9.8.8.2	Loads on Guards	Table 9.8.8.2	2015
9.8.8.3	Height of Guards	-	-
9.8.8.5	Openings in Guards	-	-
9.8.8.6	Design of Guards to Not Facilitate Climbing	-	-

^{1.} Only the applicable reference standards and code sections sited in the main body text are listed. (-) indicates that the main body text covers the full explanation of the objective.

	TABLE 1: OCCUPA	ANCY CLASSIFICATI	ON COMPLIANCE		
	2012 OBC Div. B Sections				
		3.3.5.10	9.8	9.8	
Rail Installation Description	Balusters	Group F Industrial	Part 9 Housing & Small Buildings, All guards	Part 9 Housing & Small Buildings, Max 2 dwelling	
	Sq Comp	Yes	Yes	Yes	
Standard	Square Al	Yes	Yes	Yes	
	Round Al	No	No	Yes	
	Sq Comp	Yes	Yes	Yes	
Post Mount	Square Al	Yes	Yes	Yes	
	Round Al	No	No	Yes	

Compliance Statement: It is the opinion of Boca Engineering Co., that Trex Transcend® Railing, when installed as described in this report, has demonstrated compliance with the objectives and functional statements of the listed sections of the 2012 (w/ 2020 amendments) Ontario Building Code.

Design and performance information can be found in Section 2 of this report.

This report has been prepared and reviewed on behalf of Boca Engineering Co. by:

Christopher Bowness, P.Eng., P.E.

2021-12-31



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

Evaluation

1.0 PRODUCT DESCRIPTION:

Trex Transcend® Railing is a guardrail system comprised of wood-plastic composite rails and post sleeves, aluminum or wood posts, wood-plastic composite (WPC) or aluminum balusters, glass-filled nylon brackets and metal screws.

Configuration	Balusters	No. of Footblocks	Span Between Posts	Guardrail Height	
	Square composite		Up to 91.5" (2,324 mm)		
Standard	Square aluminum	2 [†]	[96" (2,438 mm) OC]	42" (1,067 mm)	
	Round aluminum		Load-case specific		
Post mount	Square composite	2 [†]	Up to 91.5" (2,324 mm)		
	Square aluminum		[96" (2,438 mm) OC]	42" (1,067 mm)	
	Round aluminum		Load-case specific		

^{*} Footblocks are positioned at the third points of the bottom rail (i.e., at 1/2L and 1/2L, where L is the span between posts).

In the standard configuration, the railing assembly is installed between two 4×4 wood posts concealed by woodplastic composite (WPC) post sleeves, with the rail brackets fastened to the posts through the post sleeves. The wood posts are attached to the substructure.

In the post mount configuration, the railing assembly is installed between two aluminum posts concealed by wood-plastic composite (WPC) post sleeves, which slide over two post mount spacers fastened to the top and bottom of each post. In this configuration, the rail brackets are fastened to the post mount spacers through the post sleeves. The aluminum posts are welded to an aluminum baseplate with pilot holes ready to attach to the substructure.

See the attachments section at the end of this report for loading-case specific allowable post spacings, component specifications, connection details, component diagrams, and assembly drawings.

2.0 TECHNICAL EVALUATION:

2.1 INSTALLATION

- 2.1.1 Trex Transcend® Railing components with fasteners are supplied as a package. Components are manufactured to size, ready for assembly at the jobsite.
- 2.1.2 In the post mount configuration package, the aluminum posts are supplied with baseplates prepared ready with bolt holes for surface mounting to a code-compliant framing sub-structure by methods specific to the building project design. Attachment to sub-structure methods are not covered in this design evaluation.
- 2.1.3 In the standard configuration package, wood posts are not supplied by Trex and are sourced at the job site. Attachment to sub-structure methods are not covered in this design evaluation.
- 2.1.4 Manufacturer's published installation instructions are available online at: https://www.trex.com/trex-owners/customer-support/downloads/#productinstall.
- 2.1.5 Manufacturer's installation instructions, building code, and additional details in this report are to be followed.

2.2 MATERIALS PROPERTIES

The structural components of the guard system comply with the materials specifications within:

Aluminum Components: CSA S157-05, Strength Design in Aluminum.

Steel Fasteners: CSA S16-14, Design of Steel Structures.

Wood Components: CSA O86-14, Engineering Design in Wood.



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

Wood-Plastic Composite (WPC) Components: ASTM D7032-17, Standard Specification for Establishing Performance Ratings for Wood-Plastic Composite and Plastic Lumber Deck Boards, Stair Treads, Guards, and Handrails. (Materials properties testing information of WPC components is provided in Attachment 3, Table 5 of this report.

2.3 CODE SECTIONS REVIEW

OBC Div. B Description Section

3.3.1.17 All Floor Areas, Guards

Trex Transcend® Railing conforms to the dimensional and functional requirements, and the structural loading requirements, for the floor area occupancy classifications shown in Table 1 of this report.

There are no intermediate horizontal components within the infill and the system does not facilitate climbing, for where article 3.1.8.17.(4) applies when guards are protecting a level located more than one storey or 4.2 m above the adjacent level.

3.3.5.9 Industrial Occupancy, Guards

Trex Transcend® Railing with square composite or aluminum balusters conforms to the dimensional, functional and structural loading requirements of this Code section. See Table 1 of this report.

3.4.6.6 Types of Exit Facilities, Guards

Trex Transcend® Railing conforms to the dimensional, functional and structural loading requirements of this Code section for the occupancy classifications in Table 1 of this report.

4.1.1.5.(1) Structural Loads and Procedures, Design Basis

The guard system is composed of materials made of aluminum, steel, and wood, that conform to standards in Part 4, and composite materials that are not within the scope of a code-referenced standard but are within the scope of international standards CSA A500 and ASTM D7032. The design procedure under OBC 4.1.1.5 consists of a combination of acceptable solutions methods using those materials standards within the code, and an alternative solution method using the materials properties of the composite materials and system testing results to evaluate those components to the performance requirements of the Code. An expanded discussion of the design procedure is provided in Attachment 4.

4.1.3.2.(2) Limit States Design, Strength and Stability

Limit states load combinations of Table 4.1.3.2-A have been considered in this design evaluation. The common maximum loading case scenario is found to be Case 2.

Section F.24 of User's Guide – NBC 2015, Structural Commentaries directs that guards are to be designed with load combinations for ultimate limit states.

Design load combinations used in this evaluation are:

Ultimate (ULS): 1.5L + 0.4W Service (SLS): 1.0L + (0.75)0.4W



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

4.1.3.4 Limit States Design, Serviceability

Fatigue, deflection, and temperature and moisture effects serviceability limits states have been considered in the design analysis.

4.1.3.5 Limit States Design, Deflection

The deflection limits have been determined in accordance with ASTM E985-06, *Standard Specification of Permanent Metal Railing Systems and Rails for Buildings,* which is recommended for use in Section F.23 of User's Guide - NBC 2015, Structural Commentaries Part 4 of Division B.

4.1.5.14 Loads on Guards and Handrails

Table 2: Design Live Loading and Deflection Limits				
Sub-section	Load Type	Design Service Live Load	Deflection Limit	
4.1.5.14.(3)	Infill Lower Center	0.5 kN (112 lb), over 100 mm sq.	-	
4.1.5.14.(3)	Infill Middle Center	0.5 kN (112 lb), over 100 mm sq.	-	
4.1.5.14.(1)(c)	Horizontal Uniform Load Along Top Rail	0.75 kN/m (52 lb/ft)	70 mm (2.75 in)	
4.1.5.14.(6)	Vertical Uniform Load Along Top Rail	1.5 kN/m (102.7 lb/ft)	25 mm (1 in)	
4.1.5.14.(1)(c)	Concentrated Load at Midspan of Top Rail (horiz)	1.0 kN (224 lb)	70 mm (2.75 in)	
4.1.5.14.(1)(c)	Concentrated Load at Top Rail Adjacent to Post (horiz)	1.0 kN (224 lb)	-	
4.1.5.14.(1)(c)	Concentrated Load at Top of Single Post (horiz)	1.0 kN (224 lb)	89 mm (3.5 in)	

Note: Code states that these forces need not be considered to act simultaneously.

The structural design analysis has been carried out in accordance with CSA S157-05, CSA O86-14, CSA A500-16, ASTM E985-13 and ASTM D7032-17. An expanded discussion of the design procedure is provided in Attachment 4.

The deflections measured at service level loads are found not to exceed the deflection limits determined in accordance with OBC 4.1.3.5 shown in Table 2 of this report.

The system is able to resist an ultimate load of 2.25 times the service-level live load with companion wind load for each loading type shown in Table 2 of this report.

The rail system shape geometry and strength are the same in the inward and outward direction, satisfying the loading criteria of OBC 4.1.5.14.(2).

The loading criteria of OBC 4.1.5.14.(4) does not apply for the occupancy classifications cited in this report.

The reaction at the guard post base imparted to the building's main structure from the maximum loading scenario is an ultimate-level (factored) moment of 2.18 kN-m, which may be reduced to 1.58 kN-m for installations of only 2-posts. The site-specific base attachment must be designed to



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

transfer this moment to the structure.

4.1.7 Wind Load

A nominal wind load of p 1.0 kPa ($q_{1/50}$ 0.63 kPa in rough terrain at 3-storey height) has been applied in the design model with applicable factors as per OBC 4.1.7.1.(5)(a), Static Procedure for secondary structural members.

4.3.1.1 Design Basis for Wood

The design analysis of the wood components has been carried out in accordance with and complies with CSA O86-14-05, *Engineering Design in Wood*.

4.3.1.3 Termites

Refers to article 9.3. See this report commentary to OBC 9.3.2.9.

4.3.5.1 Design Basis for Aluminum

The design analysis of the aluminum components has been carried out in accordance with and complies with CSA S157-05, *Strength Design in Aluminum*.

OBC Div. B Description Section

9.3.2.9.(6)(c)(i) Termite and Decay Protection

Trex Transcend® Railing WPC components have been tested for decay and termite resistance and found to perform as well as pressure-treated Pine lumber in accordance with CAN/CSA-O80.1 for UC3.2 exterior construction.

Where OBC 4.3.1.3 or 9.3.2.9 requires termite-resistance of exterior wood components, wood posts supplied at the jobsite must comply with the respective Code requirements.

9.4.1.1.(1)(c)(i) Structural Design Requirements and Application Limits

The design methodology in this evaluation for determining conformance to Part 9 has been performed in accordance with OBC 9.4.1.1.(1)(c)(i) using the loads and deflection limits specified in Part 9.

9.8.8.2 Loads on Guards

Trex Transcend® Railing is designed to resist the minimum specified loads for the guard types listed in OBC Table 9.8.8.2, as detailed in Table 1 of this report.

9.8.8.3 Height of Guards

The top rail height of Trex Transcend® Railing is nominally 1070 mm (42 inches).

9.8.8.5 Openings in Guards

The openings between the intermediate infill members and between the bottom rail and deck surface of Trex Transcend® Railing does not exceed 100 mm (4 inches).



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

9.8.8.6 Design of Guards to Not Facilitate Climbing

There are no intermediate horizontal components within the infill and the system does not facilitate climbing, for where article 9.8.8.6 applies when guards are protecting a level located more than one storey or 4.2 m above the adjacent level.

3.0 LIMITATIONS:

- 3.1 This Evaluation is for the base code requirements of the building system as addressed in this report. In some building applications, additional performance objectives may be required by Code which must be addressed in the building design for those specific cases.
- 3.2 Design calculations, drawings, and special inspections are to be furnished for building projects by registered professionals as required by the respective jurisdictional authorities and Codes.
- 3.3 The design evaluation of Trex Transcend® Railing is of the guard system components only, installed as described in this report. Attachment of the post base to the main building structure has not been detailed or evaluated within the scope of this evaluation. The post-base reaction forces (in units of moment) for design of those elements has been discussed in comments to OBC section 4.1.5.14, and labeled on the system configuration drawings.
- 3.4 Strength and performance values apply to temperature at deck surface ranging from -29°C to 52°C.

4.0 FIRE CLASSIFICATIONS:

Aluminum components of the guard system are a *non-combustible* material as defined in OBC, Div A, 1.4.1.2. Wood-plastic composite and wood components of the guard system are a *combustible* material as defined in OBC, Div A, 1.4.1.2.

Wood-plastic composite components tested to CAN/ULC S102.2 have a Flame Spread Index of 40.

5.0 QUALITY ASSURANCE ENTITY:

The products evaluated in this report are surveyed at the approved manufacturing locations with third-party quality assurance inspections and product certification labeling by QAI Laboratories Inc.

6.0 MANUFACTURING PLANTS:

The manufacturing plants of guard rail systems covered in this evaluation are located in the following city/state locations: Winchester, VA.

7.0 LABELING:

Labeling shall be in accordance with the requirements of and bear the certification mark of the Accredited Quality Assurance Agency.

8.0 EVALUATION RENEWALS:

This Evaluation Report expires Dec 31, 2022, open to renewal, and is valid until such time as the named product(s) changes, the Quality Assurance Agency changes, the report is amended, or provisions of the Code that relate to the product change.



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

9.0 REFERENCE TESTING AND EVALUATION DOCUMENTS:

<u>Entity</u>	Entity Accreditation ¹	<u>Standards</u>	Report No.	<u>Issue Date</u>
Trex	Note 2	ASTM E935-13, ASTM D7032-17	190301-BA-2	2019-07-19
Intertek	IAS TL 144	ASTM E935-13	i1676.01-119-19-R0 ³	2019-07-16
Intertek	IAS TL 144	AWPA E10-11, ASTM D3345-08	E5777.01-119-19	2015-Nov-04
Intertek	IAS TL 144	ASTM D7032-14	C2362.01-119-19	2014-02-28
Right Testing Labs	IAS TL 859	CAN/ULC S102.2-18	RTL0028-1	2020-03-27
Trex	Note 2	ASTM D7032-17	20200818	2020-08-18
QAI	SCC 10024	Quality Assurance	B1109-1	2018-07-31

- Testing, certification, evaluation, and inspection agencies referenced have been verified to be accredited by Standards Council of Canada (www.scc.ca) or International Accreditation Service (www.iasonline.org) for the applicable scope, in good standing on the date of the evaluation, in accordance with ISO 17025 and ISO 17020 international standards for testing and inspection bodies.
- 2. Testing performed at manufacturer's R & D test facility witnessed by Boca Engineering Co.
- 3. Ultimate strength test of post, verified procedure is in accordance with ASTM E935-13.

10.0 CERTIFICATION OF INDEPENDENCE:

- Boca Engineering Co., it's employees and shareholders, do not have, nor do they intend to or will acquire, a financial interest in any company manufacturing or distributing products that they evaluate.
- 10.2 Boca Engineering Co. is not owned, operated or controlled by any company manufacturing or distributing products that they evaluate.

11.0 EVALUATION REPORT TERMS:

This report is a general evaluation of the building code section requirements as identified and applies only to the samples that were evaluated. It does not imply any endorsement or warranty, nor that the signatory Engineer is the Designer of Record of any construction project for which the information is used.

ATTACHMENTS:

1.	Components Specifications	(pg 9)
2.	Allowable Post Spacing, Assembly and Component Drawings_	(pg 10 - 16)
3.	WPC Components, Materials Properties	(pg 17)
4.	Limit States Design Procedure	(pg 18 - 19)





STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

ATTACHMENTS 1 & 2: COMPONENTS SPECIFICATIONS AND ASSEMBLY DRAWINGS


Table 3: Trex Transcend® Railing, Component Specifications				
Component	Description			
Top (crown) rail	3.312"-wide × 2.453"-high × 0.15"-thick (wall) × 91.5"-long, "crown"-shaped, extruded wood-			
Top (crown) ran	plastic composite profile			
Bottom (universal) rail	3"-wide × 2"-high × 0.13"-thick (wall) × 91.5"-long, "H"-shaped, extruded wood-plastic composite			
bottom (universal) ran	profile			
	1.418" square × 0.09"-thick (wall) × 36.375"-long, hollow, extruded wood-plastic composite tube			
	or			
Balusters	0.75" square × 0.05"-thick (wall) × 36.25"-long, hollow, extruded aluminum (6063-T6) tube			
	or			
	Ø0.75" round × 0.06"-thick (wall) × 36.25"-long, hollow, extruded aluminum (6063-T6) tube			
Baluster spacer	2.26"-wide × 0.07"-thick (wall) × 91.5"-long, extruded PVC profile with snap-fit feature for			
Daiustei spacei	installing into top and bottom rails			
Rail insert	1.61 "-wide \times 0.54 "-high \times 0.05 "-thick (wall) \times 88.75 "-long, extruded PVC profile (for use with			
Kall Illselt	aluminum balusters only)			
Rail bracket	Injection-molded glass-filled nylon bracket			
Footblock	Three-piece, threaded (for height adjustment), injection-molded glass-filled nylon foot with two-			
FOOTBIOCK	piece, decorative, injection-molded ASA sleeve			
	Nominal 4×4 (89 mm x 89 mm) wood post, D Fir-L No. 1 grade, if pressure treated must be non-			
	incised type.			
	or			
Post	2.5" square × 0.125"-thick (wall) × 41.5"-long, hollow, extruded aluminum (6063-T6) tube welded			
	on all four sides (0.25" × 0.25" fillet weld) using Ø0.045" aluminum (ER5356) wire to 4" square ×			
	0.5"-thick aluminum (6063-T6) baseplate with four Ø0.406" holes spaced 3.25" on center in the			
	corners for anchors and one Ø0.406" hole in the center (overall length: 42")			
Post mount spacer	3.63" square × 7"-long, hollow, extruded aluminum (6063-T6) tube with eight internal ribs (two			
Post mount spacer	per side) running the entire length of the profile			
Post sleeve	4.45" square × 0.15"-thick (wall), hollow, extruded wood-plastic composite tube with 12 internal			
LOST SIGENG	ribs (three per side) running the entire length of the profile			


Table 4: Trex Transcend® Railing, Fastener Specifications				
Connection	Fastener(s)			
Rail bracket to top (crown) and bottom (universal) rails	(3) #8-18 × 1-1/4", #2 square drive, pan head, self-drilling, coated steel screws			
For standard configuration				
Rail bracket to 4×4 wood (cedar) post (thru post sleeve)	(2) #8-10 × 2", #2 square drive, bugle head, coated steel wood screws			
For post mount configuration				
Post mount spacer to aluminum post	(1) #10-15 × 1", #2 square drive, flat head, self-drilling, stainless steel screw			
Rail bracket to post mount spacer (thru post sleeve)	(2) #8-15 × 1-1/4", #2 Phillips drive, pan head, stainless steel screws			













DRAWING FOR TREX TRANSCEND RAILING ENGINEERING EVALUATION REPORT — NOT FOR USE AS CONSTRUCTION DESIGN DOCUMENTS


2021/12/31 СВ FOR PUBLICATION COPYRIGHT © 2021 RESERVED. THESE PLANS AND DESIGNS ARE AT ALL TIMES THE PROPERTY OF BOCA ENGINEERING TO BE USED FOR THE PROJECT SHOWN. WRITTEN CONSENT IS REQUIRED FROM THE ENGINEER BEFORE ANY REPRODUCTION. REV DATE ISSUE APP CLIENT: PROJECT: DRAWING NO. DES CB 0078 - 2 - 3DRN TREX COMPANY, INC TREX TRANSCEND RAILING COMPONENT DRAWINGS I CL DATE DECEMBER 31, 2021 CB





A SQAURE COMPOSITE BALUSTER
NOT-TO-SCALE







C ROUND ALUMINUM BALUSTER
NOT-TO-SCALE


DRAWING FOR TREX TRANSCEND RAILING ENGINEERING EVALUATION REPORT — NOT FOR USE AS CONSTRUCTION DESIGN DOCUMENTS


COPYRIGHT © 2021 RESERVED. THESE PLA	NS AND DESIGNS ARE AT ALL TIMES THE PRO	OPERTY OF BOCA ENGINEERING TO BE	1	2021/12/31	FOR PUBLIC	CATION		СВ
	CONSENT IS REQUIRED FROM THE ENGINEER E		REV	DATE	ISSUE			APP
CLIENT:	PROJECT:	TITLE:	DRAWIN	G NO.		DES	CB	
TREV. COMPANIX, INC.				0078-	2-4	DRN		
TREX COMPANY, INC	TREX TRANSCEND RAILING	COMPONENT DRAWINGS II	DATE			DINI	CL	
				DECEMBER	31, 2021	CHK	СВ	











DRAWING FOR TREX
TRANSCEND RAILING
ENGINEERING EVALUATION
REPORT — NOT FOR USE
AS CONSTRUCTION DESIGN
DOCUMENTS

FOR PUBLICATION

ISSUE

COPYRIGHT © 2021 RESERVED. THESE PLANS AND DESIGNS ARE AT ALL TIMES THE PROPERTY OF BOCA ENGINEERING TO BE USED FOR THE PROJECT SHOWN. WRITTEN CONSENT IS REQUIRED FROM THE ENGINEER BEFORE ANY REPRODUCTION.

CLIENT:

TREX COMPANY, INC

TREX TRANSCEND RAILING

COMPONENT DRAWINGS V

REV DATE I
DRAWING NO.
0078-2-7

DATE
DECEMBER 31, 2021

2021/12/31

DES CB
DRN CL
CHK CB

СВ

APP

BOCA ENGINEERING CO. 203-1001 Cloverdale Ave, Victoria, BC, V8X 4C9 (778) 679-1375, info@bocaengineering.com

Page **16** of **19** 0078-6-3



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

ATTACHMENT 3: WPC COMPONENTS, MATERIALS PROPERTIES

ТАВ	LE 5: TREX TRANSCE	ND WOOD-PLASTIC COMPOSITE COMPONENTS, M	ATERIALS PROPERTIES F	PER ASTM D7032	
D7032 Section	Property	Requirement	Value		
4.4.1	Modulus of Rupture (MOR)	Report Value	12,400 psi ((85.5 MPa)	
4.4.2	Modulus of Elasticity (MOE)	Report Value	661,600 psi	(4562 MPa)	
			Strength (52°C):	-14%	
4.5.1	Temperature	Report % change of strength and stiffness @	Stiffness (52°C):	-14%	
4.5.1	Effect	52°C & -29°C	Strength (-29°C):	0%	
			Stiffness (-29°C):	0%	
4.5.2 Moisture Effe	Moisture Effect Report % change of strength and stiffness af 48 hrs of water submersion	Strength:	-6%		
		48 hrs of water submersion	Stiffness:	-11%	
4.6	Ultraviolet (UV)	et (UV) Report % change of strength and stiffness after	Strength:	0%	
4.0	Effect	2000 hrs of accelerated weathering	Stiffness:	0%	
	Freeze-Thaw	Report % increase/decrease of strength and	Strength:	-2%	
4.7	Effect	stiffness after three 24hr freezing cycles @ -29°C	Stiffness:	-4%	
4.8.1	Fungal Decay Resistance	Compare test block per AWPA E10 to ACQ pressure-treated lumber	Performed equivalent to ACQ-treated Pine		
4.8.2	Termite Decay Resistance	Compare test block per ASTM D3345 to ACQ pressure-treated lumber	Performed equivalent to ACQ-treated Pin		
4.9	Surface Burning Characteristics	Flame-spread index no greater than 200 ¹	40		
611	Determination of Load Reaction	Design strength and stiffness load reaction	Strength:	None	
6.1.1	Adjustment Factors	adjustment factors	Stiffness:	None	

^{1.} CAN ULC/S102.2 test results substituted for ASTM E84 test.



ATTACHMENT 4: DISCUSSION OF LIMIT STATES DESIGN PROCEDURE

Load Combinations, Load and Resistance Factors, Test Factors

Applying load combinations of live plus wind in solid and open in-fill guard systems is required by the OBC (see ref. Section F.24 of User's Guide – NBC 2015, Structural Commentaries and CSA A500-16 Section 4.2.3 Load Combinations for normative information).

Design of configured structural systems by strength testing of assemblies with a test load (safety) factor in limit states design necessitates the computation of a test load factor for the respective stress and failure type due to the various loading types of guards. Members are typically stressed to failure in bending or in shear, depending on the placement of the test load with respect to the connection/support of the member.

Test Load Factors are computed by:

Test Load Factor =
$$\frac{Combined\ Load\ Factor}{Resistance\ Factor}$$

The resistance factor is taken from the materials standard for the respective stress type (e.g. shear stress on fillet welds: on ultimate, Φ_f = 0.67, as per CSA S157).

With load combinations, the combined load factor is equal to:

Combined Load Factor = $\frac{Total\ Combined\ Ultimate\ (Factored)\ Load}{Total\ Combined\ Service\ Load}$

The test load becomes:

Test Load = (Test Load Factor) x (Total Combined Service Load)

Aluminum Components

The design analysis of the aluminum components has been carried out in accordance with and complies with CSA S157-05, *Strength Design in Aluminum*, Section 6 Methods of Analysis and Design. More specifically, Section 6.2 Testing, where it states "the adequacy of a structural assembly may be determined by tests in accordance with Section 13." Where Section 13.2.2 states, "... tests shall be conducted to accepted procedures, such as provided by an appropriate ASTM standard..." which is ASTM E935-13, *Standard Test Methods for Performance of Permanent Metal Railing Systems and Rails for Buildings*.

Following CSA S157-05 Section 13.3.1.2, the 2.25 test load factor equates to the live load factor divided by the maximum effective resistance factor of ϕ_f = 0.67 at the connections within the guard system for all loading scenarios in the NBCC Part 4 and 9, summarized in Table 2 of the report.

An individual post secured at the baseplate was taken in test, past the ultimate factored moment resulting from the maximum tributary reaction load of the factored horizontal uniform load on top rail over multiple spans.

Wood Posts

Following design procedures of CSA 086-14, the wood post has been designed to resist the maximum factored loads tributary to the post with adjustment factors for short-term loading ($K_D = 1.15$), wet-service conditions ($K_S = 0.84$) and pressure treated non-incised factor ($K_T = 1$). The 2.25 system test load factor at top of post exceeds the required effective safety factor of 1.72 calculated as the live load factor divided by the resistance factor with adjustment factors applied.

Connections in to the wood post have been tested to a proof load factor of 2.40, which equals the load factor divided by the resistance factor with adjustment factors for short-term loading ($K_D = 1.15$), wet-service conditions ($K_{SF} = 0.67$) and pressure treated non-incised factor ($K_T = 1$).



STRUCTURAL TECHNOLOGIES · DESIGN · TESTING · CODE EVALUATION

Fasteners

Common corrosion-resistant steel screws are used at the connections. The steel strength properties taken by design to CSA S16-14, *Design of Steel Structures*, are verified for the application by the system testing procedure.

Wood-Plastic Composite (WPC) Components

The wood-plastic composite (WPC) components do not fit within a code-referenced material standard, so an alternatives solution design method is employed to ensure that the material as installed meets the minimum level of performance required by Code, by following OBC Div A 1.2.1.1.(1).(b).

Appropriate published standards by organizations accredited by Standards Council of Canada have been used to complete the design.

CSA A500-16, *Building Guards*, App. Section F.2.2.2 Composites and Other Materials, Design, says "A nominal additional safety factor of 1.5 should be applied to the design loads to allow for possible ageing effects after long term weathering." Applying a 1.5 safety factor on the 1.5 load factor equates to the 2.25 test load factor, for all loading scenarios in Table 2 of this report with companion wind load applied. The test load factor of 2.25 yields an effective resistance factor of $\phi_f = 0.67$ for all stress types in the WPC components.

ASTM D7032-17, Standard Specification for Establishing Performance Ratings for Wood-Plastic Composite and Plastic Lumber Deck Boards, Stair Treads, Guards, and Handrails, has methods for testing the effects of possible strength loss due to temperature, aging, moisture, and freeze-thaw. The standard also has procedures for guard system testing, which were used and modified as applicable to match the loading requirements of OBC Part 4 and Part 9.

The applicable objectives and functional statements from OBC Div A Part 2 and 3, taken from the referenced Div B acceptable solutions, that the WPC components have been verified to satisfy are:

Objectives are to limit the risk of injury, illness, or damages, caused by:

Symbol	Description
OS2.1	Ultimate loads on building elements
OS2.3	Damage or deterioration of building elements
OS2.4	Vibration or deflection of building elements
OH4	Illness attributed to vibration and deflection
OP2.1	Loads bearing on the building elements that exceed their loadbearing capacity
OP2.3	Damage to or deterioration of building elements
OP2.4	Vibration or deflection of building elements

The building elements are to perform the following functions:

Symbol	Description
F20	Support and withstand expected loads
F21	Limit dimensional change
F22	Limit movements under expected loads and forces
F80	Resist deterioration from expected service conditions
F21 F22	Limit dimensional change Limit movements under expected loads and forces